

**ПЛЁНКА  
ПОЛИВИНИЛХЛОРИДНАЯ  
ПЛАСТИФИЦИРОВАННАЯ  
ТЕХНИЧЕСКАЯ  
МАРКА ОН**

**PLASTICIZED  
PVC  
FILM  
COMMERCIAL GRADE  
ON TYPE**

**НАЗНАЧЕНИЕ**

Предназначена для консервации машин, механизмов, электродвигателей, авиационных и других изделий, а также используется в конструкции кабелей для создания защитной оболочки. Намного прочнее полиэтиленовой пленки.

**ОПИСАНИЕ**

Лента не имеет отверстий, пузырьков, трещин и надрывов на кромках. Поверхность рулона гладкая. Цвет-натуральный.

**МЕТОД ПРОИЗВОДСТВА**

Плѐнка изготавливается каландрованием поливинилхлоридной композиции.

**ТЕХНИЧЕСКИЕ ТРЕБОВАНИЯ  
ГОСТ 16272-79 с изм. 1-3**

Наименование показателей	Высший сорт	1 сорт
Прочность при разрыве, МПа (кгс/см <sup>2</sup> ) - вдоль - поперѐк	18,0 (183) 15,0 (153)	11,8 (120) 9,8 (100)
Относительное удлинение при разрыве, %, не менее	200	140
Температура хрупкости, °С, не выше	-20	-25
Выпускается следующих размеров: длина плѐнки в рулоне, м, не более толщина плѐнки, мм ширина, мм вес рулона, кг, не более	500 0,23±0,04 1200±20 50	

**ПОСТАВКА**

ЖД вагон 30- 40 т или самовывоз.  
Пленка не является опасным грузом.

**ГАРАНТИЙНЫЙ СРОК ХРАНЕНИЯ**

Высший сорт - 5 лет со дня изготовления,  
первый сорт - 3 года со дня изготовления.

**APPLICATION**

It is used for preservation of machines, mechanisms, motors and aircraft articles; as well as in the construction of cables for creation of sheath. Plasticized PVC film excels polyethylene film in its strength.

**DESCRIPTION**

It does not contain holes, bubbles, cracks through all surface and edge tears. The surface of a roll is smooth. The surface of a roll is smooth. The color is natural.

**PRODUCTION**

The tape is produced by calendering of PVC compound.

**SPECIFICATION  
GOST 16272-79, rev. ver. 1-3**

Name of Properties	Superior grade	1 st grade
Rupture strength, МPa (kgf/cm <sup>2</sup> ), no less than - in longitudinal direction - in transversal direction	18.0 (183) 15.0 (153)	11.8 (120) 9.8 (100)
Elongation at rupture, %, no less than	200	140
Brittleness temperature, °C, no higher than	-20	-25
It is produced in the following dimensions: Length in a roll, m, no more than Thickness of film, mm Width, mm Weight of a roll, no more than, kg	500 0,23±0,04 1200±20 50	

**DELIVERY**

Rail wagon of 30-40 t or self transportation.  
It is not dangerous cargo.

**GUARANTEED STORAGE LIFE**

Superior grade - 5 years since the date of production  
First grade - 3 years since the date of production.